



# NADIR® NP010 P

## “Nanofiltration” Membrane

NADIR® NP010 is a polyethersulfone (PES) membrane that exhibits nanofiltration characteristics when exposed to high pressure. Its stabilized molecular weight cut-off is in the range of 1,000-1,200 Daltons after operation at 40 bar (580 psi). NP010 membrane is durable enough to be used in concentrated acid environments and caustic recovery systems with a pH range of 0 - 14. NP010 membrane sheet is available in dry flat sheet rolls and is FDA compliant.

### Membrane Characteristics

Membrane Chemistry	Backing Material	Na <sub>2</sub> SO <sub>4</sub> Rejection Bounds (%) <sup>a</sup>
Polyethersulfone (PES)	Polypropylene	35 - 75

Permeability LMH/bar (GFD/psi) <sup>b</sup>	Thickness (µm)	pH Range
≥ 200 (≥ 8.1)	210 – 250	0.0 – 14.0

a Test conditions: 5,000 ppm Na<sub>2</sub>SO<sub>4</sub>, 40 bar (580 psi), 20°C (68°F). Membrane specifications may change without notice as design revisions occur.

b Test conditions: Clean water, 40 bar (580 psi), 20°C (68°F).

### Important Information

**Standard Sizes:** NADIR flat sheet membrane is available in an A4 sample size of 210 mm x 297 mm (8.27 in x 11.69 in) and in a nominal roll size of 150 m x 1016 mm (492 ft x 40.0 in). Custom lengths may be available on request.

**Initial Flush:** MICRODYN-NADIR recommends flushing membrane for 30 minutes and discarding permeate during the flush prior to operation.

**Storage:** Membrane shipped dry should be stored away from direct sunlight in a cool, dry place. Please see *Membrane Storage Guide – Flat Sheet Membrane* (TSG-O-011).

## Solving Unmet Needs with Customized Products



Headquarters  
MICRODYN-NADIR GmbH  
Building D512  
Kasteler Straße 45  
65203 Wiesbaden  
Germany  
info@microdyn-nadir.de  
www.microdyn-nadir.de

USA Office  
MICRODYN-NADIR US, Inc.  
93 South La Patera Lane  
Goleta, CA 93117  
USA  
info@microdyn-nadir.com  
www.microdyn-nadir.com/en  
www.microdyn-nadir.com/trisep

China Office  
MICRODYN-NADIR (Xiamen) Co. Ltd.  
No. 66 Jinting North Road Xinglin  
Xiamen, China 361022  
infochina@microdyn-nadir.com

Singapore Office  
MICRODYN-NADIR Singapore Pte. Ltd.  
18 Tuas Avenue 8  
639233 Singapore  
info@microdyn-nadir.com