



NADIR® UH030 P

Ultrafiltration Membrane

With a nominal molecular weight cut-off (M.W.C.O.) of 30,000 Daltons, NADIR® UH030 flat sheet is a hydrophilic polyethersulfone (PESH) membrane that can be configured in a wide variety of element designs for food, dairy and process separations as well as water purification. UH030 membrane sheet is available in dry flat sheet rolls and is FDA compliant.

Membrane Characteristics

Membrane Chemistry	Backing Material	Nominal M.W.C.O (Da)	Thickness (µm)
Hydrophilic Polyethersulfone (PESH)	Polypropylene	30,000	210 - 250

Permeability LMH/bar (GFD/psi) ^a	PVP K30 Retention (%) ^b	pH Range	Chlorine Tolerance ^c
≥ 35.0 (≥ 1.4)	78.0 – 86.0	0.0 – 14.0	200 ppm (sanitization) at pH ≥ 10.5

a Test conditions: Clean water, 4 bar (58 psi), 20°C (68°F), crossflow operation. Membrane specifications may change without notice as design revisions occur.

b Test conditions: 2% PVP K30, 4 bar (58 psi), 20°C (68°F), crossflow operation.

c For daily short term cleaning: maximum 50°C (125°F), 30 min.

Important Information

Standard Sizes: NADIR flat sheet membrane is available in an A4 sample size of 210 mm x 297 mm (8.27 in x 11.69 in) and in a nominal roll size of 150 m x 1016 mm (492 ft x 40.0 in). Custom lengths may be available on request.

Initial Flush: MICRODYN-NADIR recommends flushing membrane for 30 minutes and discarding permeate during the flush prior to operation.

Storage: Membrane shipped dry should be stored away from direct sunlight in a cool, dry place. Please see *Membrane Storage Guide – Flat Sheet Membrane* (TSG-O-011).

Solving Unmet Needs with Customized Products



Headquarters
MICRODYN-NADIR GmbH
Building D512
Kasteler Straße 45
65203 Wiesbaden
Germany
info@microdyn-nadir.de
www.microdyn-nadir.de

USA Office
MICRODYN-NADIR US, Inc.
93 South La Patera Lane
Goleta, CA 93117
USA
info@microdyn-nadir.com
www.microdyn-nadir.com/en
www.microdyn-nadir.com/trisep

China Office
MICRODYN-NADIR (Xiamen) Co. Ltd.
No. 66 Jinting North Road Xinglin
Xiamen, China 361022
infochina@microdyn-nadir.com

Singapore Office
MICRODYN-NADIR Singapore Pte. Ltd.
18 Tuas Avenue 8
639233 Singapore
info@microdyn-nadir.com